



LAMINATED VENEER LUMBER (LVL)

WAREHOUSE B/149 ORCHARD RD, CHESTER HILL NSW 2162
1800 367 675

info@formplyaustralia.com.au
www.formplyaustralia.com.au

A BOUT US

Formply Australia is an Australian company focused on providing supplies and products for the formwork industry. All our products are sourced from suppliers of legally managed forest plantations, who are members of the international Forest Stewardship Council (FSC) program.

We are located in the central industrial precinct of Chester Hill, and offer a delivery service within the Sydney Metropolitan area as well as a convenient collection service at our warehouse.

Formply Australia is continuously sourcing new products to bring you the highest quality formwork products from our warehouse to your worksite. Our aim is to create a comprehensive centralised warehouse to cater for all your formwork needs.



LAMINATED VENEER LUMBER (LVL)

Formply Australia LVL timbers are a structural laminated veneer lumber used in the Australian construction industry. These LVLs have been manufactured in accordance with Australian and International Accreditations AS/NZ 6669-07 and AS/NZ4357.0 which are FSC Certified.

Our LVL timbers are a type of high-strength engineered timber that can be used as an alternative to solid timber, concrete or steel for structural purposes. They are manufactured by bonding rotary peeled or wood veneers sliced thinly under heat and pressure.

FEATURES AND BENEFITS

- Sourced from legally managed forest plantations.
- Each beam is painted bright orange for moisture protection and branded for easy identification purposes.
- LVL provides a cost-effective and sustainable building material, delivering high structural reliability and strength.
- Less prone to shrinking or warping.



DENSITY / TOLERANCES
560 kg/m³

THICKNESS
-0/+10 mm

LENGTH
-0/+10 mm

WIDTH
0/+2 mm

SUITABLE APPLICATIONS: Formwork Joists and Bearers / Soldiers and Walers**SPECIFICATIONS:****Veneer**

Species: Larch and Pine
Thickness: 3.2mm

Joints

Face and core scarfed veneers

Glue Phenolformaldehyde

Bond:

Type A (Marine) AS/NZS 2098 and AS /2754

Density

760kg/m³

Additional Processing

Arrised edge and orange water resistant coating

FORMPLY AUSTRALIA E12 CONCRETE FORMWORK JOIST SPAN TABLES

This table displays Formply Australia E12 joists supporting concrete formwork, with a deflection criterion of Class III (span/270).

CONCRETE SLAB THICKNESS (mm)	FORMPLY E12 MEMBER SIZE (mm)	FORMPLY E12 JOIST SPACING (mm)						FORMPLY E12 JOIST SPACING (mm)					
		225	300	400	450	480	600	225	300	400	450	480	600
		FORMPLY E12 MAXIMUM SINGLE SPAN (m)						FORMPLY E12 MAXIMUM CONTINUOUS SPAN (m)					
100	95 X 45	1.95	1.75	1.6	1.5	1.5	1.4	2.4	2.15	1.95	1.9	1.8	1.65
	95 X 47	1.95	1.8	1.6	1.55	1.5	1.4	2.45	2.2	2.0	1.9	1.85	1.65
	95 X 63	2.15	1.95	1.8	1.7	1.65	1.55	2.7	2.45	2.2	2.1	2.1	1.9
	95 X 65	2.2	2.0	1.8	1.75	1.7	1.55	2.7	2.45	2.25	2.15	2.1	1.95
	130 X 75	3.15	2.85	2.6	2.5	2.45	2.25	3.9	3.55	3.2	3.1	3.05	2.8
	130 X 77	3.2	2.9	2.6	2.5	2.45	2.3	3.95	3.6	3.25	3.1	3.05	2.85
	150 X 75	3.65	3.3	3.0	2.9	2.8	2.6	4.5	4.1	3.7	3.6	3.5	3.25
	150 X 77	3.7	3.35	3.05	2.9	2.85	2.65	4.55	4.15	3.75	3.6	3.55	3.3
150	95 X 45	1.8	1.65	1.5	1.45	1.4	1.3	2.25	2.05	1.85	1.75	1.7	1.5
	95 X 47	1.85	1.7	1.5	1.45	1.45	1.3	2.3	2.1	1.9	1.8	1.75	1.55
	95 X 63	2.05	1.85	1.7	1.6	1.6	1.45	2.55	2.3	2.1	2.0	1.95	1.8
	95 X 65	2.05	1.85	1.7	1.65	1.6	1.5	2.55	2.35	2.1	2.05	2.0	1.85
	130 X 75	3.0	2.7	2.45	2.35	2.3	2.15	3.7	3.35	3.05	2.95	2.85	2.65
	130 X 77	3.0	2.75	2.5	2.4	2.35	2.15	3.75	3.4	3.05	2.95	2.9	2.7
	150 X 75	3.45	3.15	2.85	2.75	2.65	2.5	4.25	3.9	3.5	3.4	3.3	3.05
	150 X 77	3.5	3.15	2.85	2.75	2.7	2.5	4.3	3.9	3.55	3.4	3.35	3.1
200	95 X 45	1.75	1.55	1.45	1.35	1.35	1.25	2.15	1.95	1.75	1.65	1.6	1.45
	95 X 47	1.75	1.6	1.45	1.4	1.35	1.25	2.2	2.0	1.8	1.7	1.65	1.45
	95 X 63	1.95	1.75	1.6	1.55	1.5	1.4	2.4	2.2	2.0	1.9	1.85	1.7
	95 X 65	1.95	1.8	1.6	1.55	1.5	1.4	2.45	2.2	2.0	1.95	1.9	1.75
	130 X 75	2.85	2.6	2.35	2.25	2.2	2.05	3.5	3.2	2.9	2.8	2.75	2.55
	130 X 77	2.85	2.6	2.35	2.25	2.2	2.05	3.55	3.25	2.95	2.8	2.75	2.55
	150 X 75	3.3	3.0	2.7	2.6	2.55	2.35	4.05	3.7	3.35	3.2	3.15	2.9
	150 X 77	3.3	3.0	2.75	2.6	2.55	2.4	4.1	3.75	3.4	3.25	3.2	2.95
300	95 X 45	1.6	1.45	1.3	1.25	1.25	1.15	2.0	1.8	1.8	1.6	1.45	1.3
	95 X 47	1.65	1.45	1.35	1.3	1.25	1.15	2.0	1.85	1.85	1.65	1.5	1.35
	95 X 63	1.8	1.65	1.5	1.4	1.4	1.3	2.25	2.0	2.0	1.85	1.7	1.55
	95 X 65	1.8	1.65	1.5	1.45	1.4	1.3	2.25	2.05	2.05	1.85	1.75	1.55
	130 X 75	2.6	2.4	2.15	2.05	2.05	1.9	3.25	2.95	2.95	2.7	2.5	2.3
	130 X 77	2.65	2.4	2.2	2.1	2.05	1.9	3.3	3.0	3.0	2.7	2.55	2.35
	150 X 75	3.05	2.75	2.5	2.4	2.35	2.2	3.75	3.4	3.4	3.1	2.9	2.65
	150 X 77	3.05	2.8	2.5	2.4	2.35	2.2	3.8	3.45	3.45	3.15	2.95	2.7

400	95 X 45	1.5	1.35	1.25	1.2	1.15	1.05	1.85	1.7	1.45	1.4	1.35	1.2
	95 X 47	1.5	1.4	1.25	1.2	1.15	1.1	1.9	1.7	1.5	1.5	1.35	1.2
	95 X 63	1.7	1.55	1.4	1.35	1.3	1.2	2.1	1.9	1.7	1.7	1.6	1.4
	95 X 65	1.7	1.55	1.4	1.35	1.3	1.2	2.1	1.9	1.75	1.75	1.6	1.45
	130 X 75	2.45	2.25	2.0	1.95	1.9	1.75	3.05	2.75	2.5	2.5	2.35	2.1
	130 X 77	2.5	2.25	2.05	1.95	1.9	1.8	3.4	2.8	2.55	2.55	2.4	2.15
	150 X 75	2.85	2.6	2.35	2.25	2.2	2.05	3.55	3.2	2.9	2.9	2.75	2.45
	150 X 77	2.85	2.6	2.35	2.25	2.2	2.05	3.55	3.25	2.95	2.95	2.75	2.5
500	95 X 45	1.4	1.3	1.15	1.1	1.1	1.0	1.75	1.6	1.35	1.3	1.25	1.1
	95 X 47	1.45	1.3	1.2	1.15	1.1	1.05	1.8	1.6	1.4	1.3	1.25	1.15
	95 X 63	1.6	1.45	1.3	1.25	1.25	1.15	2.0	1.8	1.6	1.5	1.45	1.3
	95 X 65	1.6	1.45	1.3	1.25	1.25	1.15	2.0	1.8	1.65	1.55	1.5	1.35
	130 X 75	2.35	2.1	1.9	1.85	1.8	1.65	2.9	2.6	2.4	2.3	2.2	2.0
	130 X 77	2.35	2.15	1.95	1.85	1.8	1.7	2.9	2.65	2.4	2.3	2.25	2.0
	150 X 75	2.7	2.45	2.2	2.15	2.1	1.95	3.35	3.05	2.75	2.65	2.55	2.3
	150 X 77	2.7	2.45	2.25	2.15	2.1	1.95	3.35	3.05	2.8	2.65	2.6	2.3
600	95 X 45	1.35	1.25	1.1	1.05	1.05	0.95	1.7	1.5	1.3	1.2	1.15	1.05
	95 X 47	1.35	1.25	1.15	1.1	1.05	1.0	1.7	1.5	1.3	1.25	1.2	1.05
	95 X 63	1.5	1.4	1.25	1.2	1.15	1.1	1.9	1.5	1.5	1.45	1.4	1.25
	95 X 65	1.5	1.4	1.25	1.2	1.2	1.1	1.9	1.75	1.55	1.45	1.4	1.25
	130 X 75	2.2	2.0	1.85	1.75	1.7	1.6	2.75	2.5	2.25	2.15	2.1	1.85
	130 X 77	2.25	2.05	1.85	1.75	1.75	1.6	2.8	2.5	2.3	2.2	2.1	1.9
	150 X 75	2.55	2.35	2.1	2.05	2.0	1.85	3.2	2.9	2.65	2.5	2.4	2.15
	150 X 77	2.6	2.35	2.15	2.05	2.0	1.85	3.2	2.9	2.65	2.5	2.45	2.15
1000	95 X 45	1.15	1.05	0.95	0.90	0.90	0.85	1.4	1.2	1.05	1.0	0.95	0.85
	95 X 47	1.2	1.1	1.0	0.95	0.60	0.85	1.45	1.25	1.1	1.1	1.0	0.85
	95 X 63	1.3	1.2	1.1	1.05	1.0	0.95	1.65	1.45	1.25	1.25	1.15	1.0
	95 X 65	1.35	1.2	1.1	1.05	1.05	0.95	1.65	1.45	1.25	1.25	1.15	1.05
	130 X 75	1.95	1.75	1.6	1.5	1.5	1.4	2.4	2.15	1.9	1.9	1.7	1.55
	130 X 77	1.95	1.75	1.6	1.55	1.5	1.4	2.4	2.2	1.9	1.9	1.75	1.55
	150 X 75	2.25	2.05	1.85	1.75	1.75	1.6	2.75	2.5	2.15	2.15	2.0	1.75
	150 X 77	2.25	2.05	1.85	1.8	1.75	1.6	2.8	2.55	2.2	2.2	2.0	1.8

FORMPLY AUSTRALIA E12 CONCRETE FORMWORK BEARER SPAN TABLES

This table displays 6 for Formply Australia E12 bearers supporting concrete formwork, with a deflection criterion of Class III (span/270).

CONCRETE SLAB THICKNESS (mm)	FORMPLY E12 MEMBER SIZE (mm)	FORMPLY E12 BEARER SPACING (mm)						FORMPLY E12 BEARER SPACING (mm)					
		900	1200	1500	1800	2100	2400	900	1200	1500	1800	2100	2400
		FORMPLY E12 MAXIMUM SINGLE SPAN (m)						FORMPLY E12 MAXIMUM CONTINUOUS SPAN (m)					
100	95 X 45	1.2	1.1	1.0	0.95	0.85	0.80	1.3	1.15	1.0	0.95	0.85	0.75
	95 X 47	1.2	1.1	1.0	0.95	0.90	0.80	1.35	1.15	1.05	0.95	0.85	0.80
	95 X 63	1.35	1.2	1.15	1.05	1.0	0.95	1.55	1.35	1.2	1.1	1.0	0.95
	95 X 65	1.35	1.25	1.15	1.05	1.0	0.95	1.6	1.4	1.25	1.1	1.05	0.95
	130 X 75	1.95	1.8	1.65	1.55	1.5	1.4	2.35	2.05	1.8	1.65	1.55	1.45
	130 X 77	2.0	1.8	1.65	1.55	1.5	1.4	2.4	2.05	1.85	1.7	1.55	1.45
	150 X 75	2.3	2.05	1.9	1.8	1.7	1.65	2.7	2.35	2.1	1.9	1.75	1.65
	150 X 77	2.3	2.1	1.95	1.8	1.75	1.65	2.75	2.4	2.15	1.95	1.8	1.7
150	95 X 45	1.15	1.05	0.95	0.85	0.80	0.75	1.25	1.05	0.95	0.85	0.75	0.70
	95 X 47	1.15	1.05	0.95	0.90	0.80	0.75	1.25	1.1	0.95	0.90	0.80	0.70
	95 X 63	1.25	1.15	1.05	1.0	0.95	0.90	1.45	1.25	1.15	1.05	0.95	0.90
	95 X 65	1.3	1.15	1.1	1.0	0.95	0.90	1.5	1.3	1.15	1.05	0.95	0.90
	130 X 75	1.85	1.7	1.55	1.45	1.4	1.35	2.2	1.9	1.7	1.55	1.45	1.35
	130 X 77	1.9	1.7	1.6	1.5	1.4	1.35	2.25	1.95	1.75	1.55	1.45	1.35
	150 X 75	2.15	1.95	1.8	1.7	1.6	1.55	2.55	2.2	1.95	1.8	1.65	1.55
	150 X 77	2.2	1.95	1.85	1.7	1.65	1.55	2.6	2.25	2.0	1.8	1.7	1.55
200	95 X 45	1.1	1.0	0.90	0.80	0.75	0.70	1.15	1.0	0.90	0.80	0.70	0.65
	95 X 47	1.1	1.0	0.90	0.85	0.75	0.70	1.2	1.05	0.90	0.80	0.75	0.65
	95 X 63	1.2	1.1	1.0	0.95	0.90	0.85	1.4	1.2	1.05	0.95	0.90	0.80
	95 X 65	1.2	1.1	1.05	0.95	0.90	0.85	1.4	1.2	1.1	1.0	0.90	0.85
	130 X 75	1.8	1.6	1.5	1.4	1.35	1.25	2.1	1.8	1.6	1.45	1.35	1.25
	130 X 77	1.8	1.6	1.5	1.4	1.35	1.3	2.1	1.8	1.65	1.5	1.35	1.30
	150 X 75	2.05	1.85	1.75	1.6	1.55	1.45	2.4	2.1	1.85	1.7	1.55	1.45
	150 X 77	2.05	1.9	1.75	1.65	1.55	1.5	2.45	2.1	1.9	1.7	1.6	1.5
300	95 X 45	1.0	0.90	0.80	0.75	0.70	0.65	1.05	0.90	0.80	0.70	0.60	0.55
	95 X 47	1.0	0.90	0.85	0.75	0.70	0.65	1.1	0.95	0.80	0.70	0.65	0.60
	95 X 63	1.1	1.0	0.95	0.90	0.80	0.75	1.25	1.1	0.95	0.85	0.80	0.70
	95 X 65	1.15	1.0	0.95	0.90	0.80	0.75	1.25	1.1	1.0	0.90	0.80	0.70
	130 X 75	1.65	1.5	1.35	1.3	1.2	1.15	1.9	1.65	1.45	1.3	1.2	1.1
	130 X 77	1.65	1.5	1.4	1.3	1.25	1.15	1.9	1.65	1.45	1.35	1.25	1.15
	150 X 75	1.9	1.7	1.6	1.5	1.4	1.3	2.15	1.9	1.7	1.55	1.4	1.3
	150 X 77	1.9	1.75	1.6	1.5	1.45	1.35	2.2	1.9	1.7	1.55	1.45	1.3

400	95 X 45	0.95	0.85	0.75	0.70	0.65	0.60	0.95	0.80	0.70	0.60	0.55	0.50
	95 X 47	0.95	0.85	0.75	0.70	0.65	0.60	1.0	0.85	0.70	0.65	0.55	0.50
	95 X 63	1.05	0.95	0.85	0.80	0.75	0.70	1.15	1.0	0.90	0.75	0.70	0.65
	95 X 65	1.05	0.95	0.90	0.80	0.75	0.70	1.15	1.0	0.90	0.80	0.70	0.65
	130 X 75	1.55	1.4	1.3	1.2	1.1	1.05	1.75	1.5	1.35	1.2	1.1	1.0
	130 X 77	1.55	1.4	1.3	1.2	1.15	1.05	1.75	1.5	1.35	1.25	1.1	1.0
	150 X 75	1.8	1.6	1.5	1.4	1.3	1.2	2.0	1.75	1.55	1.4	1.25	1.15
	150 X 77	1.8	1.65	1.5	1.4	1.3	1.25	2.05	1.75	1.55	1.45	1.3	1.15
500	95 X 45	0.90	0.80	0.70	0.65	0.60	0.55	0.90	0.75	0.65	0.55	0.50	0.45
	95 X 47	0.90	0.80	0.70	0.65	0.60	0.55	0.90	0.75	0.65	0.55	0.50	0.50
	95 X 63	1.0	0.90	0.80	0.75	0.70	0.65	1.05	0.90	0.80	0.70	0.65	0.55
	95 X 65	1.0	0.90	0.85	0.75	0.70	0.65	1.1	0.95	0.80	0.70	0.65	0.60
	130 X 75	1.45	1.3	1.2	1.15	1.05	1.0	1.6	1.4	1.25	1.1	1.0	0.90
	130 X 77	1.45	1.35	1.25	1.15	1.05	1.0	1.65	1.4	1.25	1.1	1.0	0.90
	150 X 75	1.7	1.5	1.4	1.3	1.2	1.15	1.85	1.6	1.45	1.25	1.15	1.05
	150 X 77	1.7	1.55	1.45	1.35	1.25	1.15	1.9	1.65	1.45	1.3	1.15	1.05
600	95 X 45	0.85	0.75	0.65	0.60	0.55	0.50	0.85	0.65	0.60	0.50	0.45	0.45
	95 X 47	0.85	0.75	0.65	0.60	0.55	0.50	0.85	0.70	0.60	0.55	0.50	0.45
	95 X 63	0.95	0.85	0.75	0.70	0.65	0.60	1.0	0.85	0.75	0.65	0.60	0.55
	95 X 65	0.95	0.85	0.80	0.70	0.65	0.60	1.0	0.90	0.75	0.65	0.60	0.55
	130 X 75	1.4	1.25	1.15	1.05	1.0	0.90	1.5	1.3	1.15	1.0	0.90	0.80
	130 X 77	1.4	1.25	1.15	1.1	1.0	0.95	1.55	1.3	1.15	1.0	0.90	0.85
	150 X 75	1.6	1.45	1.35	1.25	1.15	1.05	1.75	1.5	1.3	1.15	1.05	0.95
	150 X 77	1.6	1.45	1.35	1.25	1.15	1.05	1.75	1.55	1.35	1.2	1.05	0.95
1000	95 X 45	0.70	0.60	0.55	0.50	0.45	0.40	0.65	0.50	0.45	0.40	0.40	0.35
	95 X 47	0.70	0.60	0.55	0.50	0.45	0.40	0.65	0.55	0.45	0.40	0.40	0.35
	95 X 63	0.80	0.70	0.65	0.60	0.55	0.50	0.80	0.65	0.55	0.50	0.45	0.45
	95 X 65	0.80	0.70	0.65	0.60	0.55	0.50	0.80	0.65	0.55	0.50	0.45	0.45
	130 X 75	1.2	1.05	0.95	0.85	0.80	0.75	1.25	1.0	0.85	0.75	0.70	0.65
	130 X 77	1.2	1.1	0.95	0.90	0.80	0.75	1.25	1.05	0.90	0.80	0.70	0.65
	150 X 75	1.4	1.25	1.1	1.0	0.95	0.85	1.45	1.15	1.0	0.90	0.80	0.75
	150 X 77	1.4	1.25	1.1	1.0	0.95	0.90	1.45	1.2	1.0	0.90	0.85	0.75

- Notes:
1. Member deflections are limited to span/270 (Class III formwork limit in accordance with AS 3610.1-2010). However, this does not guarantee compliance with Class III criteria since other components outside the scope of this table contribute to the form face deflection.
 2. Spans allow for a stacked materials loading of 4kPa.
 3. Members are assumed to have a moisture content of <15%. The span table shall not be relied upon where members are used in a wet condition (moisture content >15%. For moisture contents >15% designers must incorporate the deformation factor (j2) from AS1720.1-2010.
 4. Interpolation of spans for immediate concrete thicknesses is permitted. Extrapolation is not permitted.
 5. Continuous span members include 2 or more equally spaced spans with uniformly distributed loading.

SAFE WORKING PRACTICES

Formply Australia is dedicated to safe working practises for sites and employees, we encourage you to follow the below listed recommendations.

- Personal Protective Equipment for head, eyes, hands and feet.
- Follow the correct product procedure specifications.
- Ensure worksite area is free of unnecessary debris to avoid risks.
- Conduct appropriate risk hazard assessment.



STORAGE/HANDLING RECOMMENDATIONS

We also encourage you to follow the below mentioned storage and handling recommendations to ensure your product maintains its durability, performance and longevity.

- Ensure LVL beams are stored in a dry, well-ventilated area.
- Ensure cut edges are sealed with an acrylic paint.
- Ensure spacers are layered between wet members and sheets are allowed to dry out.
- Ensure LVL beams are not used over spans greater than the recommendations listed.



By Royal Charter

Certificate

This is to certify that **Formply Australia**

ABN **64 152 810 592**

Head Office Address **5A Melissa St
Auburn
New South Wales
2144
Australia**

Holds Certificate Number **BMP 717540**

Is authorised to use the BSI registered Benchmark Product Certification Trademark, on products identified in the Product Certification Schedule that is attached to this Product Certification Certificate. Such products have been Type Tested and are manufactured under the Product Certification Requirements monitored by BSI to ensure that the manufacturing process has the capability to consistently produce products in compliance with and are Certified to:

AS/NZS 4357.0:2005 (R2016) Structural laminated veneer lumber Specifications

For and on behalf of BSI

Marc Barnes, Managing Director, BSI Group ANZ Pty Ltd

Originally registered
04/02/2020

Latest issue
30/08/2021

Expiry date
03/02/2025



...making excellence a habit.

The use of this certificate and of the Benchmark Product Certification mark trademark is subject to the Client complying with the BSI Mark Requirements, and Terms and Conditions. BSI Group ANZ Pty Ltd, Suite 1, Level 1, 54 Waterloo Road, Macquarie Park, NSW 2113
The validity of this certificate can be checked at website: www.bsi-global.com/clientdirectory and the JASANZ website: www.jas-anz.org/register. This certificate remains the property of BSI and must be returned upon its request. Template updated September 2020.



By Royal Charter

Schedule

This schedule supports the Product Certification Certificate for	Formply Australia
ABN	64 152 810 592
Head Office Address	5A Melissa St Auburn New South Wales 2144 Australia
Holds Certificate Number	BMP 717540
Standard	AS/NZS 4357.0:2005 (R2016) Structural laminated veneer lumber Specifications
Issue date	30/08/2021

Model	BSI Review Date	Description
95 x 45 LVL 11 F 14	31/07/2019	Laminated Veneer Lumber for General Structural Use 95 x 45 Mixed Species Laminated Veneer Lumber E 12530 MPa, f'b 59 MPa, f's 4.8 MPa, f'p 7.0 f't 40.2 MPa, f'c 36.8 MPa F14 on edge F17 on Flat, A-Bond E ₀
95 x 65 LVL 14 F 17	31/07/2019	Laminated Veneer Lumber for General Beams used on edge only 95 x 65 Larch Laminated Veneer Lumber E 14561 MPa, f'b 63 MPa, f's 5.2 MPa, f'p 7.6 F17 A-Bond E ₀
150 x 77 LVL 11 F 14	31/07/2019	Laminated Veneer Lumber for General Beams used on edge only 150 x 77 Larch Laminated Veneer Lumber E 12878 MPa, f'b 57 MPa, f's 4.8 MPa, f'p 9.5 F14 A-Bond E ₀

BMP 717540
30/08/2021 Page 2 of 2



...making excellence a habit.

The use of this certificate and of the Benchmark Product Certification mark trademark is subject to the Client complying with the BSI Mark Requirements, and Terms and Conditions. BSI Group ANZ Pty Ltd, Suite 1, Level 1, 54 Waterloo Road, Macquarie Park, NSW 2113
The validity of this certificate can be checked at website: www.bsi-global.com/clientdirectory and the JASANZ website: www.jas-anz.org/register. This certificate remains the property of BSI and must be returned upon its request. Template updated September 2020.